

Technical Data Sheet

Date Revision
09/01/2002

Révision
0

Material : Our / Reference

2187V/NK

POUDMET Copper powder

21 GSG-100/2,9

Copper magnesium powder, water atomised,
irregular shape

Inspection Characteristic	Unit	Lower Limiting Value	Upper Limiting Value	Desired Value	Indicative Value	Méthode
Physical						
Physical analysis :						
Sieve analysis ISO 4497 cumulative :						
> 160 µm	%		0,50			IN.V.1007
> 40 µm	%	40,00	55,00			IN.V.1007
Apparent density ISO 3923/1 - 2,5 mm	g/cm3	2,70	2,90			IN.V.1010
Flowability ISO 4490 - 2,5 mm	s		30,0			IN.V.1004
Chemical						
Chemical analysis :						
Copper (Cu)	%	99,30000				IN.V.1137
Hydrogen Loss ISO 4491/2	%		0,300			IN.V.1134

FDS : Poudre de cuivre

All statements, technical information and recommendations herein are based on tests and data which our Company believes to be currently reliable. The accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto. Product characteristics may change due to technical development and / or improvement of production methods.

Adresse postale
Poudmet S.A.S.
BP 90319
F 60332 LIANCOURT CEDEX

Tél. : + 33 (0) 3 44 69 12 31
Fax : + 33 (0) 3 44 69 12 30
E-mail : info.poudmet@poudmet.fr

S.A.S. au capital de 500.000 €
SIRET Beauvais 528 945 660 000 25
TVA FR24 528 945 660
RCS Paris 528 945 660
APE 2444 Z