

**Technical Data Sheet**

Date Revision  
09/09/2013

Révision  
1

Material : Our / Reference

2631ZAK

**POUDMET Copper Powder**

**21 GS-325**

Copper powder, water atomised, irregular shape.

Inspection Characteristic	Unit	Lower Limiting Value	Upper Limiting Value	Desired Value	Indicative Value	Méthode
<b>Physical</b>						
Physical analysis :						
Sieve analysis ISO 4497 cumulative :						
> 63 µm	%		0,10			IN.V.1007
< 45 µm	%	95,00				IN.V.1007
Apparent density ISO 3923/1 - 2,5 mm	g/cm3	2,90	3,60			IN.V.1010
<b>Chemical</b>						
Chemical analysis :						
Copper (Cu)	%	99,00000				IN.V.1024
Hydrogen Loss ISO 4491/2	%		0,900			IN.V.1134

FDS : 21GS,21GSG,22BB,22VN, fibres Cu

All statements, technical information and recommendations herein are based on tests and data which our Company believes to be currently reliable. The accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto. Product characteristics may change due to technical development and / or improvement of production methods.

Adresse postale  
Poudmet S.A.S.  
BP 90319  
F 60332 LIANCOURT CEDEX

Tél. : + 33 (0) 3 44 69 12 31  
Fax : + 33 (0) 3 44 69 12 30  
E-mail : info.poudmet@poudmet.fr

S.A.S. au capital de 500.000 €  
SIRET Beauvais 528 945 660 000 25  
TVA FR24 528 945 660  
RCS Paris 528 945 660  
APE 2444 Z