

Technical Data Sheet

Date Revision 08/03/2013	Révision 4
-----------------------------	---------------

Material : Our / Reference

2334ZAL

POUDMET Bronze powder

25 GR 90/10-16

Bronze powder, water atomised, irregular shape

Inspection Characteristic	Unit	Lower Limiting Value	Upper Limiting Value	Desired Value	Indicative Value	Méthode
Physical						
Physical analysis :						
Sieve analysis ISO 4497 residue :						
> 850 µm	%		1,00			IN.V.1007
850 / 425 µm	%	10,00	30,00			IN.V.1007
425 / 150 µm	%	50,00	70,00			IN.V.1007
< 150 µm	%	5,00	30,00			IN.V.1007
Apparent density ISO 3923/1 - 2,5 mm	g/cm3	2,50	3,10			IN.V.1010
Tap density ISO 3953	g/cm3	3,00	3,65			IN.V.1009
Chemical						
Chemical analysis :						
Copper (Cu)	%	89,50000	91,00000			
Tin (Sn)	%	9,00000	10,50000			IN.V.1138
Lead (Pb)	%		0,10000			IN.V.1138
Others	%		0,50000			IN.V.1138

FDS : Poudre de cupro-alliages

All statements, technical information and recommendations herein are based on tests and data which our Company believes to be currently reliable. The accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto. Product characteristics may change due to technical development and / or improvement of production methods.

Adresse postale
Poudmet S.A.S.
BP 90319
F 60332 LIANCOURT CEDEX

Tél. : + 33 (0) 3 44 69 12 31
Fax : + 33 (0) 3 44 69 12 30
E-mail : info.poudmet@poudmet.fr

S.A.S. au capital de 500.000 €
SIRET Beauvais 528 945 660 000 25
TVA FR24 528 945 660
RCS Paris 528 945 660
APE 2444 Z