

### Technical Data Sheet

Date Revision  
05/09/2013

Révision  
3

Material : Our / Reference

2379UAN

**POUDMET Tin powder**

**30 GN-250**

Tin powder, air atomised, spheroid shape,  
tin content 99.85% min.

Inspection Characteristic	Unit	Lower Limiting Value	Upper Limiting Value	Desired Value	Indicative Value	Méthode
<b>Physical</b>						
Physical analysis :						
Sieve analysis (air jet-sieving) cumulat						
> 200 µm	%		0,10			IN.V.1008
> 63 µm	%		5,00			IN.V.1008
Apparent density ISO 3923/1 - 5,0 mm	g/cm <sup>3</sup>	3,40	4,00			IN.V.1010
<b>Chemical</b>						
Chemical analysis :						
Pb content 500 ppm max						
Cd ,Cr ,Hg 50 ppm max each						

FDS : 30GN, POUDMET.

All statements, technical information and recommendations herein are based on tests and data which our Company believes to be currently reliable. The accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto. Product characteristics may change due to technical development and / or improvement of production methods.

Adresse postale  
Poudmet S.A.S.  
BP 90319  
F 60332 LIANCOURT CEDEX

Tél. : + 33 (0) 3 44 69 12 31  
Fax : + 33 (0) 3 44 69 12 30  
E-mail : info.poudmet@poudmet.fr

S.A.S. au capital de 500.000 €  
SIRET Beauvais 528 945 660 000 25  
TVA FR24 528 945 660  
RCS Paris 528 945 660  
APE 2444 Z