

Technical Data Sheet

Date Revision
13/01/2014

Révision
1

Material : Our / Reference

2145YAQ **POUDMET Tin powder 60 BG**

Tin powder, air atomised, spheroid shape
tin content 99.85%.

Inspection Characteristic	Unit	Lower Limiting Value	Upper Limiting Value	Desired Value	Indicative Value	Méthode
Physical						
Physical analysis :						
Sieve analysis (air jet-sieving) residue						
> 106 µm	%		0,50			IN.V.1008
106 / 75 µm	%		10,00			IN.V.1008
75 / 45 µm	%	10,00	30,00			IN.V.1008
< 45 µm	%	60,00	80,00			IN.V.1008
Apparent density ISO 3923/1 - 5,0 mm	g/cm3	4,00	4,40			IN.V.1010
Chemical						
Chemical analysis :						
Hydrogen Loss ISO 4491/2	%		0,100			IN.V.1134

FDS : 30GN, POUDMET.

All statements, technical information and recommendations herein are based on tests and data which our Company believes to be currently reliable. The accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto. Product characteristics may change due to technical development and / or improvement of production methods.

Adresse postale
Poudmet S.A.S.
BP 90319
F 60332 LIANCOURT CEDEX

Tél. : + 33 (0) 3 44 69 12 31
Fax : + 33 (0) 3 44 69 12 30
E-mail : info.poudmet@poudmet.fr

S.A.S. au capital de 500.000 €
SIRET Beauvais 528 945 660 000 25
TVA FR24 528 945 660
RCS Paris 528 945 660
APE 2444 Z