

Technical Data Sheet

Date Revision
07/06/2013

Révision
1

Material : Our / Reference

10488

Bronze powder spherical

CuSn11 < 0.063 mm

Inspection Characteristic	Unit	Lower Limiting Value	Upper Limiting Value	Desired Value	Indicative Value	Méthode
Physical						
Physical analysis :						
Sieve analysis ISO 4497 residue :						
> 63 µm	%		5,00			
< 63 µm	%	95,00				
Apparent density ISO 3923/1 - 2,5 mm	g/cm ³	4,00	5,05			
Chemical						
Chemical analysis :						
Tin (Sn)	%	10,00000	11,50000			
Phosphorus (P)	%	0,27000	0,43000			
Copper (Cu) : Balance %						

FDS :

All statements, technical information and recommendations herein are based on tests and data which our Company believes to be currently reliable. The accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto. Product characteristics may change due to technical development and / or improvement of production methods.

Adresse postale
Poudmet S.A.S.
26, rue du moulin
F 60140 BAILLEVAL

Tél. : + 33 (0) 3 44 69 12 31
Fax : + 33 (0) 3 44 69 12 30
E-mail : info.poudmet@poudmet.fr

S.A.S. au capital de 500.000 €
SIRET Beauvais 528 945 660 000 25
TVA FR24 528 945 660
RCS Paris 528 945 660
APE 2444 Z