

Technical Data Sheet

Date Revision
05/03/2003

Révision
3

Material : Our / Reference

2228VNI

POUDMET POUDMIX CuSn PX 672

Press ready premix.

Inspection Characteristic	Unit	Lower Limiting Value	Upper Limiting Value	Desired Value	Indicative Value	Méthode
Physical						
Physical analysis :						
Sieve analysis ISO 4497 cumulative :						
> 200 µm	%		1,00			IN.V.1007
> 160 µm	%		10,00			IN.V.1007
Apparent density ISO 3923/1 - 2,5 mm	g/cm ³	2,85	3,05			IN.V.1010
Flowability ISO 4490 - 2,5 mm	s		45,0			IN.V.1004
Chemical						
Chemical analysis :						
Tin (Sn)	%	9,00000	11,00000			IN.V.1138
Carbon (C)	%			0,10		
Wax	%			0,40		
Frittage						
Sintering :						
Green density	N/mm ²			6,08		IN.V.1020
Green strength	N/mm ²	5,00				IN.V.1022
Sintering atmosphere 30% H ₂ /70% N ₂						
Dewaxing at 600°C	min			10,00		IN.V.1150
Sintering at 810°C	min			11,50		IN.V.1150
Dimensional change	%	0,10	0,30			IN.V.1149
Dimensional change of standard	%					IN.V.1149
Radial crushing strength	N/mm ²	100				IN.V.1022
Radial crushing strength of standard	N/mm ²					IN.V.1022

FDS :

All statements, technical information and recommendations herein are based on tests and data which our Company believes to be currently reliable. The accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto. Product characteristics may change due to technical development and / or improvement of production methods.

Adresse postale
Poudmet S.A.S.
BP 90319
F 60332 LIANCOURT CEDEX

Tél. : + 33 (0) 3 44 69 12 31
Fax : + 33 (0) 3 44 69 12 30
E-mail : info.poudmet@poudmet.fr

S.A.S. au capital de 500.000 €
SIRET Beauvais 528 945 660 000 25
TVA FR24 528 945 660
RCS Paris 528 945 660
APE 2444 Z