

Technical Data Sheet

Date Revision
13/01/2014

Révision
3

Material : Our / Reference

2152ZJP

POUDMET Solder powder

SnAg3

Silvered tin powder, air atomised, spheroid shape.

Inspection Characteristic	Unit	Lower Limiting Value	Upper Limiting Value	Desired Value	Indicative Value	Méthode
Physical						
Physical analysis :						
Sieve analysis ISO 4497 residue :						
> 75 µm	%		0,50			IN.V.1008
75 / 45 µm	%	5,00	15,00			IN.V.1008
45 / 25 µm	%	15,00				IN.V.1008
< 25 µm	%	55,00				IN.V.1008
Apparent density ISO 3923/1 - 5,0 mm	g/cm3					IN.V.1010
Chemical						
Chemical analysis :						
Silver (Ag)	%	3,00000	3,50000			
Tin (Sn) : Balance %						
Hydrogen Loss ISO 4491/2	%		0,200			IN.V.1134

FDS : SnAg

All statements, technical information and recommendations herein are based on tests and data which our Company believes to be currently reliable. The accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto. Product characteristics may change due to technical development and / or improvement of production methods.

Adresse postale
Poudmet S.A.S.
BP 90319
F 60332 LIANCOURT CEDEX

Tél. : + 33 (0) 3 44 69 12 31
Fax : + 33 (0) 3 44 69 12 30
E-mail : info.poudmet@poudmet.fr

S.A.S. au capital de 500.000 €
SIRET Beauvais 528 945 660 000 25
TVA FR24 528 945 660
RCS Paris 528 945 660
APE 2444 Z