

Technical Data Sheet	
Date Revision	Révision
0	

Material : Our / Reference

10505

**Brass powder**

**V AS < 0.045 mm**

Inspection Characteristic	Unit	Lower Limiting Value	Upper Limiting Value	Desired Value	Indicative Value	Méthode
<b>Physical</b>						
Physical analysis :						
Sieve analysis ISO 4497 residue :						
> 45 µm	%		5,00			
< 45 µm	%	95,00				
Apparent density ISO 3923/1 - 2,5 mm	g/cm3					
<b>Chemical</b>						
Chemical analysis :						
Copper (Cu)	%	70,00000	72,00000			
Aluminium (Al)	%	0,15000	0,54000			
Zinc ( Zn ) : BALANCE %						

FDS :

All statements, technical information and recommendations herein are based on tests and data which our Company believes to be currently reliable. The accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto. Product characteristics may change due to technical development and / or improvement of production methods.

Adresse postale  
Poudmet S.A.S.  
26, rue du moulin  
F 60140 BAILLEVAL

Tél. : + 33 (0) 3 44 69 12 31  
Fax : + 33 (0) 3 44 69 12 30  
E-mail : info.poudmet@poudmet.fr

S.A.S. au capital de 500.000 €  
SIRET Beauvais 528 945 660 000 25  
TVA FR24 528 945 660  
RCS Paris 528 945 660  
APE 2444 Z