



Management  
System  
ISO 9001:2015

www.tuv.com  
ID 910506865

### Technical Data Sheet

Date Revision  
30/05/2002

Révision  
0

Material : Our / Reference

1862

**Boron powder**

**92 BO-300**

Inspection Characteristic	Unit	Lower Limiting Value	Upper Limiting Value	Desired Value	Indicative Value	Méthode
<b>Physical</b>						
Physical analysis :						
Apparent density ISO 3923/1 - 2,5 mm	g/cm <sup>3</sup>	0,30	0,40			
Average particle size Fisher dF	µm					
Specific surface Method BET	m <sup>2</sup> /g	10,00				
<b>Chemical</b>						
Chemical analysis :						
Boron (B)	%	95,00000				
Oxygen (O <sub>2</sub> ) ISO 4491/4	%		2,20000			
Magnesium (Mg)	%		0,80000			

FDS :

All statements, technical information and recommendations herein are based on tests and data which our Company believes to be currently reliable. The accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto. Product characteristics may change due to technical development and / or improvement of production methods.

Adresse postale  
Poudmet S.A.S.  
26, rue du moulin  
F 60140 BAILLEVAL

Tél. : + 33 (0) 3 44 69 12 31  
Fax : + 33 (0) 3 44 69 12 30  
E-mail : info.poudmet@poudmet.fr

S.A.S. au capital de 500.000 €  
SIRET Beauvais 528 945 660 000 25  
TVA FR24 528 945 660  
RCS Paris 528 945 660  
APE 2444 Z