



Technical Data Sheet	
Date Revision 29/08/2011	Révision 0

Material : Our / Reference

10686

**Copper powder**

**CHL10**

Inspection Characteristic	Unit	Lower Limiting Value	Upper Limiting Value	Desired Value	Indicative Value	Méthode
<b>Physical</b>						
Physical analysis :						
Sieve analysis ISO 4497 residue :						
> 45 µm	%		5,00			
< 45 µm	%	95,00				
Apparent density ISO 3923/1 - 2,5 mm	g/cm3	0,90	1,10			
Specific surface Fisher	cm <sup>2</sup> /g			2 000,00C		
<b>Chemical</b>						
Chemical analysis :						
Oxygen (O2) ISO 4491/4	%		0,25000			
Produced of KE-Copper min. 99,9 %						

FDS :

All statements, technical information and recommendations herein are based on tests and data which our Company believes to be currently reliable. The accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto. Product characteristics may change due to technical development and / or improvement of production methods.

Adresse postale  
Poudmet S.A.S.  
26, rue du moulin  
F 60140 BAILLEVAL

Tél. : + 33 (0) 3 44 69 12 31  
Fax : + 33 (0) 3 44 69 12 30  
E-mail : info.poudmet@poudmet.fr

S.A.S. au capital de 500.000 €  
SIRET Beauvais 528 945 660 000 25  
TVA FR24 528 945 660  
RCS Paris 528 945 660  
APE 2444 Z